

Levanna Restoration Lumber

RECLAIMED SOFTWOODS

Premium Grade Barn Siding

GRADE DESCRIPTION

Grain & Grain Density:

A random mix of flat-sawn and vertical grain with no restriction to grain density.

Heartwood:

A random mixture of heartwood and sapwood.

Thickness:

A random mixture ranging from 1/2" – 7/8" is typical.

Color:

Weather Grey Siding: As-found surfaces include a full range of natural browns, grays and black. Hints of old paint may be present.
Painted Siding: Painted siding may contain lead-based paint. A Clear Finish Encapsulation Is Recommended.

Texture:

Face will vary from rough-sawn or planed to heavily weathered. Premium siding is ripped and chopped. Fresh wood edges will show.

Stains/Fading:

Staining from ferrous metal fasteners may be present. Color and patina will vary.

Knots:

Sound, tight knots without restrictions; some chipped, cracked, broken and open knots will be present.

Checks:

Checks are allowed so long as boards remain in tact for installation.

Holes:

Holes from nail, bolt, & other mechanical fasteners may be present. Holes from open knots reaching 2" in diameter may be present.

Moisture:

Siding is air-dried with a typical moisture content of 12-14%. Heat Treating or Kiln Drying must be specified. An up charge will apply.

Finish:

Product is provided unfinished.

LEED Certification:

MR 4.1 & 4.2 (Material Reuse)
MR 5.1 & 5.2 (Materials)

Auburn, NY 13021

Office: (315) 252-6817 • Mobile: (315) 567-1646 • info@LevannaRL.com • www.LevannaRL.com